

_Vanadium Aluminum 65:35

GfE Spec. 2000 154

Application

VAI 65:35 is used as master alloy for the production of titanium alloys

Production method

Metallothermic reduction

Quality

Material magnetically separated

Size

0.25 - 6.3 mm

Packaging

In sealed steel drums

Chemical Analysis in wt%

V	62 - 68
Al	32 - 38
B	≤0.01
C	≤0.05
Fe	≤0.5
Mo	≤0.1
Ni	≤0.05
P	≤0.05
S	≤0.05
Si	≤0.4
H	≤0.02
N	≤0.05
O	≤0.3

No. 8 | August 2023