

**A-Chromium Powder High Purity**  
GfE Spec. 2025 405

**Application**

For electrical switch contacts, coatings on cutting devices, brake discs

**Production method**

Aluminothermic reduction

**Size**

0 - 80  $\mu\text{m}$   
with max. 5% > 80  $\mu\text{m}$

**Packaging**

In sealed steel drums



**Chemical Analysis in wt%**

Cr	$\geq 99.3$
Al	$\leq 0.2$
Fe	$\leq 0.2$
K	$\leq 0.01$
Na	$\leq 0.01$
S	$\leq 0.02$
Si	$\leq 0.1$
C	$\leq 0.02$
O	$\leq 0.2$
N	$\leq 0.03$

No. 1 | January 2022